

PRODUCT PROFILE

Rev.1 11/23



Commercial Heavy 430FR is a high quality knitted flame retardant shade fabric designed for tension structures, awnings and shade sails specifically for commercial architectural applications; supplied in bulk rolls.

- Strong HDPE 100% recyclable fabric won't rot or absorb moisture.
- Stentered (heat-set) to reduce shrinkage and for ease of fabrication.
- Certified to California State Fire Marshall CSFM 1237.1 and complies with NFPA701 across all colour variants.
- 12-year UV degradation warranty on fabric.
- · 100% Lead and Phthalate free
- · Engineered in Australia to meet the harsh climate

FABRIC PROPERTIES

(AS 2001.2.13) mass per unit

Nominal fabric mass 430 gsm ± 20 Approximate thickness 1.6 mm

ROLL SPECIFICATIONS

Nominal width:

Length:

Approx. roll weight:

Approx. roll diameter:

Core diameter:

3.0m (unfolded)

40m

54 kg

0.30 m

76 mm

USAGE INSTRUCTIONS

Do not use against flames.

Contact with organic solvents, halogens or highly acidic substances may reduce the service life of the fabric and void the warranty.

Biaxial elastic material properties available on request.

SUGGESTED SPECIFICATION

Shade cloth fabric shall be compliant to Australian standard AS 4174:2018 and shall be GALE Commercial Heavy 430 FR knitted with HDPE monofilament offering a UVE Protection Category of "Effective".

FLAMMABILITY

Part 2 & 3 certificates available on request

(AS 1530.2) Part 2 - Flammability of Materials Flammability Index (Range 0-100)

(AS 1530.3) Part 3 - Flammability of MaterialsIgnitability Index (Range 0-20)13Spread of Flame Index (Range 0-10)8Heat Evolved Index (Range 0-10)5Smoke Developed Index (Range 0-10)7

PERFORMANCE

(AS 2001.2.3.1-2001) Maximum Force and Elongation - Strip MethodMaximum Force - Warp (Mean)1400 N/50mmElongation at Maximum Force - Warp (Mean)70 %Maximum Force - Weft (Mean)1300 N/50mmElongation at Maximum Force (Mean)144 %

(AS 2001.2.3.2-2001) Breaking Force - Grab Test

Breaking Force – Warp (Mean) 1600 N Breaking Force – Weft (Mean) 1800 N

(AS 2001.2.10-1986) Tear Resistance - Wing Rip Method

 Wing Tear – Warp (mean)
 255 N

 Wing Tear – Weft (mean)
 272 N

(AS 2001.2.4) Bursting Pressure – Hydraulic Diaphragm Method Bursting Pressure (mean) 3200 kPa

(AS 2001.2.19-1988) Bursting Force – Ball Burst MethodBursting Force (mean) 1955 N

(AS 4174:2018) Shade Protection Fabric Performance

Colour	Cover Factor	Shade Factor	UV-Vis Trans %	UVR Trans %	UVR Block %	UVE %	Protection Category
Aquatic Blue	86	85.7	14.3	14.1	85.9	85	Effective
Black	87	87.5	12.5	12.5	87.5	87	Effective
Bright Green	85	84.1	15.9	14.6	85.4	84	Effective
Brunswick Green	84	84.5	15.5	15.5	84.5	84	Effective
Charcoal	86	86.8	13.2	13.1	86.9	86	Effective
Deep Ochre	87	87.0	13.0	12.9	87.1	86	Effective
Desert Sand	85	79.8	20.2	14.7	85.3	84	Effective
Emerald	86	86.2	13.8	13.5	86.5	86	Effective
Natural	87	75.9	24.1	12.7	87.3	87	Effective
Navy Blue	87	87.4	12.6	12.5	87.5	87	Effective
Orange	85	75.5	24.5	14.8	85.2	84	Effective
Red	86	75.5	24.5	13.8	86.2	86	Effective
Royal Purple	87	86.8	13.2	12.5	87.5	87	Effective
Steel Grey	86	85.9	14.1	13.3	86.7	86	Effective
White	86	71.5	28.5	13.8	86.2	86	Effective
Yellow	86	74.1	25.9	13.3	86.7	86	Effective















ANZ MIDDLE EAST AMERICAS ASIA EUROPE P 1800 331 521 P +971 4 881 7114 P 1800 560 4667 P 1800 331 521 P 1800 560 4667

www.galecommercial.com